



General technical information

switch from waste to QUALITY products



material

100% high quality recycled plastic residue, mainly from the nutrition and packaging industry

Composition: LDPE (Low Density Polyethylene)
HDPE (High Density Polyethylene)
PP (Polypropylene)

production

The different plastics are ground, mixed and fused together under high temperatures and pressed into moulds. During production, the material is mass coloured in order to obtain a homogenous colour.



finish & look

STANDARD : the surface is knot free, evenly coloured throughout and shows a faced, slightly shining structure.

IMPRESS : the material has a non removable wood grain surface

BASIC : the material and its surface are rougher than the standard and impress finish.



available colours

Govaplast

Ural Black
Quartz Brown
Canyon Brown
Sand Beige
Atlas Beige
Mineral Grey
Ash Grey
Andes Green

Govaplast Horse

Ural Black
Quartz Brown
Canyon Brown
Sand Beige
Atlas Beige
Mineral Grey
Ash Grey
Andes Green

Govaplast Home +

Ural Black
Quartz Brown
Sand Beige
Atlas Beige
Mineral Grey*
Ash Grey

*Not for Govawall

Govaplast Street

Ural Black
Quartz Brown
Sand Beige
Mineral Grey
Andes Green

Govaplast Play

Quartz Brown
Sand Beige
Andes Green

Govaplast Technic

Ural Black

tolerance

In products made of recycled plastic, tolerances of about 2% on the measurements are possible.

workability

Comparable to wood: screwing, nailing, sawing, drilling, planing, milling, stapling etc. The product may bend when cut lengthwise.

Recommendations: drill at low speed
rough-drill before screwing
preferably saw with a circular saw (WIDIA)

properties

quality reclaimed



100% plastic waste



Completely recyclable



Coloured throughout



Solid core

born to be outdoor



Weatherproof



UV resistant



Non absorbing



Non slip material



Everlasting

everlasting appearance



Maintenance free



Graffiti resistant



Natural texture



Rot-proof



Removable scratches

stronger than ever



Flexible



Easy to process



Splinter-free



Impact resistant

Results screw extraction test:

screw dimensions: 4 x 50 mm
drawing speed 10 mm / min (no predrilled holes)
test with 5 screws

Tensile force average 4365 N +/- 14% deviation

1. Tensile test according to ISO 527-2 (2012)

modulus	719	Mpa
yield	7,8	Mpa
tensile strenght	17,2	Mpa
stretch break	478	%

2. Flexural test according to ISO 178 (2019)

Elasticity module short term	940N/mm2
Elasticity module long term	150N/mm2

3. Hardness measurement according to ISO 2039-2 32,09 HB

4. Impact according to ISO 179-1 (2000) notched 65,6 kJ/m²

5. a. Vicat temperature according to ISO 306/A50 115,20 °C

b. MFI according to ISO1133 (2005) 4,3 g/10 min

6. Liquid absorption according to ISO 62 0,29 %

7. Density according to ISO 1183-1 (2004) 0,960 kg/dm³

8. Linear expansion coefficient 0,109 mm/m/°C

9. Flamability tests

according to DIN 4102 part 1	fire class B2
according to EN ISO 13501-1: 2007+A1:2009	fire class E _{fl}

10. Slip resistance decking boards

according to EN 1341 pendulum test (dry) in PTV *	86 - 96
according to EN 1341 pendulum test (wet) in PTV *	29 - 47
* PTV 25-35 = moderate slip potential	
* PTV 36+ = low slip potential	
according to DIN 51130 ramp test (wet) R-classification	R10

11. Pressure test

from 1700 N/cm ²	light pressure
from 3100 N/cm ²	impression
from 6300 N/cm ²	no more resistance

commercial product	chemical substance	results
liquid bleach	NaOCl (min. 36°)	no discolouration or modification
lubricating oil	synthetic engine oil	no discolouration or modification
salad oil	corn oil	no discolouration or modification
degreaser	acetone butanone tetrachloroethylene diluted sulphuric acid diluted soda	no discolouration or modification
pool water	saturated solution of trichloro isocyanic acid	no discolouration or modification
white spirit	mixture of aliphatic hydrocarbons	no discolouration or modification
moss killer	saturated solution of iron sulphate and disodium - EDTA	no discolouration or modification
fat	heated deep-frying fatl at 180°C	Slight discolouration because of superficial melting of the plastic. <i>Remark:</i> Test with boiling oil. In the real situation oil splashes are not 180°C when they reach the boards.

test temperature : 20° C (room temperature)

test duration: 24 hours

visual test

tests executed with concentrated or less diluted solutions than available in retail

Notes:

1. Apart from extensive internal research, the material was tested by: Hogeschool Gent (CPMT), DMT (Fachstelle für Brandschutz), FGK (Forschungsinstitut für anorganische Werkstoffe, Glas/Keramik), Geos (constructive testing), VKC (Vlaams Kunststof Centrum)

2. These test results are referring to the tested objects only. The detailed test reports can be requested for inspection.